

PBEV SERIES - Deep Cycle AGM

PBEV12-14 (12V14Ah)

Specification

Cells Per Unit	6
Voltage Per Unit	12V
Capacity	14Ah@20hour-rate to 1.75V per cell @25°C
Weight	Approx. 4.20 Kg (Tolerance ±5%)
Internal Resistance	≤13.0 mΩ (Full Charge Condition @25°C)
Terminal	Default F2, F1 Optional
Max. Discharge Current	210A (5 sec)
Cold Cranking Ampere(CCA)	140A
Maxi. Charging Current	4.2A
Reference Capacity	C ₃ 10.5Ah C ₅ 11.6Ah C ₁₀ 13.2Ah C ₂₀ 14.0Ah
Float Charging Voltage	13.7 V~13.9 V @ 25°C Temperature Compensation: -3mV/°C/Cell
Cycle Use Voltage	14.6 V~14.8 V @ 25°C Temperature Compensation: -4mV/°C/Cell
Operating Temperature Range	Discharge: -20°C~60°C Charge: 0°C~50°C Storage: -20°C~60°C
Normal Operating Temperature Range	25°C ±5°C
Self Discharge	PB Valve Regulated Lead Acid (VRLA) batteries can be stored for up to 6 months at 25°C and then recharging is recommended. Monthly Self-discharge ratio is less than 3% at 25°C lease charged batteries before using.
Container Material	A.B.S. UL94-HB, UL94-V0 Optional.



EV (Electric Vehicle) series is specially designed for frequent discharge deep cycle application. By using the specially designed active material, strong grids and thick plate construction, the EV series battery offers reliable performance in high load situations and could provide competitive cycle performance. It is suitable for Electric Vehicle and Golf cart, Floor Machines, Forklifts, Aerial lifts, Robotics, Marine, RV, Mobility and Medical Equipment, and most outdoor application.

Intertek



ISO14001



ISO9001



Constant Current Discharge Characteristics : A(25)C

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	58.53	38.37	28.58	16.43	9.645	5.503	3.886	3.039	2.536	1.714	1.418	0.728
1.65V	56.37	37.10	27.73	16.09	9.463	5.409	3.827	2.997	2.505	1.695	1.403	0.721
1.70V	53.55	35.43	26.60	15.63	9.221	5.285	3.748	2.941	2.463	1.669	1.384	0.713
1.75V	49.80	33.20	25.09	15.01	8.892	5.115	3.639	2.865	2.405	1.634	1.358	0.700
1.80V	44.82	30.21	23.06	14.16	8.438	4.880	3.489	2.758	2.325	1.585	1.321	0.683
1.85V	38.10	26.13	20.26	12.95	7.792	4.544	3.273	2.604	2.208	1.513	1.267	0.658


Constant Power Discharge Characteristics : W/Cell(25)C

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	99.26	65.23	49.97	29.84	18.03	10.43	7.423	5.834	4.889	3.347	2.787	1.433
1.65V	98.12	64.73	49.49	29.65	17.88	10.33	7.354	5.784	4.853	3.320	2.764	1.423
1.70V	94.26	62.51	47.90	28.98	17.48	10.12	7.220	5.689	4.782	3.274	2.729	1.407
1.75V	89.24	59.63	45.84	28.11	16.94	9.841	7.041	5.562	4.686	3.211	2.680	1.384
1.80V	81.71	55.21	42.72	26.79	16.16	9.436	6.777	5.374	4.545	3.122	2.611	1.352
1.85V	70.69	48.60	38.07	24.75	15.03	8.834	6.385	5.094	4.331	2.987	2.508	1.305




(Note) The above characteristics data are average values obtained within three charge/discharge cycle not the minimum values.

The battery must be fully charged before the capacity test. The C₂₀ should reach 95% after the first cycle and 100% after the third cycle.


Dimensions




T2 Terminal




Charge Characteristic Curve for Cycle Use(IIUU)




Charge Characteristic Curve For Cycle Use(UII)




Discharge Characteristics Curve




Relationship Between Charging Voltage and Temperature




Cycle Life in Relation to Depth of Discharge




Storage Characteristics



Relationship of OCV And State of Charge(20°C)



Temperature Effects on Capacity



(Note) All above information shall be changed without prior notice, PB reserves the right to explain and update the latest information.